

# Coating Stabilizers

Long-lasting protection against degradation caused by light and heat

Used in a wide number of industries, coatings not only provide countless items with color and texture, but also enhance their appearance and prolong their life.

In order to protect coatings against the harmful effects of light and heat, SONGWON offers a comprehensive range of high-value, high-performance coating stabilizers for numerous substrates, including steel, wood, ceramics, special composites, plastic films and plastic parts used in the inks, automotive and transportation, decorative and architectural, furniture and flooring, industrial and agricultural industries among others.

It's all about **the chemistry™**

 **SONGWON**

# SONGWON offers a broad range of coating stabilizers

## Antioxidants (AOs)

AOs prevent thermally induced degradation of polymers in coatings, adhesives and inks during high-temperature processing, curing and stoving as well as in end use.

Under the brand name SONGNOX® CS, SONGWON offers a wide and diversified portfolio of AOs, ranging from primary (sterically hindered) phenolic products to secondary thioesters and phosphites.

SONGNOX® CS 1010 and SONGNOX® CS 1076, the most commonly used AOs, provide protection against thermal degradation over a vast range of temperatures in numerous different coatings, plastics, adhesives and sealants applications.

SONGWON secondary AOs exhibit synergistic effects with primary antioxidants. SONGWON offers blends of primary and secondary AOs such as SONGNOX® CS 147B, SONGNOX® CS 41B, and many other primary and secondary AOs that can be mixed in different ratios, depending on requirements.

For applications that require heat stabilization during mixing, extrusion or curing and for paints that are cured or stoved at high temperatures, as required for powder and coil coatings, for example, SONGNOX® CS 6260, SONGNOX® CS 1680 and SONGNOX® CS PQ phosphite AOs are the products of choice.

AOs are non-regenerative: both primary and secondary types are consumed during the reaction and left ineffective afterwards. For longer-term effects, the use of certain hindered amine light stabilizers (HALS) is preferred, due to the cyclic nature of their reaction.

## UV Absorbers (UVAs)

UVAs prevent the degradation of coating systems by converting the absorbed light into heat. There are several well-known chemical classes of UVA broadly used in coatings, inks and adhesives: 2-hydroxyphenyl-benzophenone or BP type (for example SONGSORB® CS 81), 2-(2-hydroxyphenyl)-benzotriazole or BTZ type (for example SONGSORB® CS 1130 and SONGSORB® CS 928), and 2-hydroxyphenyl-triazine or HPT type (for example SONGSORB® CS 1577). SONGWON's range also includes an oxanilide-type UVA, SONGSORB® CS 312, which is suitable for solvent-borne and powder coatings.

Every UVA has its own specific photo-physical primary and secondary properties. Filter efficiency, for example, varies, depending on the product's extinction coefficient, chemical class and molecular weight. To cater for customer-specific filtering needs, SONGWON offers a broad range of UVAs that can be used alone or in combination with other products such as SONGSORB® CS HALS or SONGNOX® CS AOs.

The synergistic effect of UVA and HALS is particularly beneficial for outdoor conditions, where UVAs alone cannot efficiently provide adequate protection, being unable to prevent discoloration and other detrimental effects on coatings.

The filter effect of a coating, expressed as Absorbance A, is influenced by film thickness and UVA concentration. The thinner the coating, the higher the amount of UVA required. Another important criterion for selection of the right UVA for the final application is its photo-permanence, which is basically a measure of the resistance of the UVA to degradation. Products vary in their tendency to chemical loss and migration out of the coating matrix. Typically, BP types such as SONGSORB® CS 81 can be used in applications with moderate requirements in terms of long-term stability, while for applications requiring medium to higher long-term stability, BTZ types, such as SONGSORB® CS 928, are needed.



## Hindered Amine Light Stabilizers (HALS)

HALS are radical scavengers: they trap radicals formed in the coating layer during exposure to light. Since this mechanism is independent of film thickness, HALS are particularly suitable for the surface of a coating, where UVAs offers less protection. In addition, HALS provide protection against surface defects such as cracking and water permeability. SONGWON offers liquid difunctional HALS such as SONGSORB® CS 292, one of the most frequently used products on the market, and SONGSORB® CS 5100, which is non-interacting and has lower basicity.

SONGWON also offers special-feature HALS such SONGSORB® CS 144 and SONGSORB® CS 119, which have triboelectric charging properties and are the products of choice for powder coatings.

The cyclic nature of the stabilization mechanism of HALS means that they typically show higher and longer-term efficiency. While HALS are usually not effective in preventing thermal degradation (for which SONGWON antioxidants are the products of choice), they are well suited as light stabilizers and thanks to their regenerative nature they function over much longer time scales.

Oligofunctional HALS such as SONGSORB® CS 622 can also effectively function as long-term heat stabilizers under moderate thermal exposure.



# Product range selection guide

|                     |                  | Automotive<br>Inks | Industrial<br>Wood | Construction | Solventborne | Waterborne | UV curing<br>Powder |
|---------------------|------------------|--------------------|--------------------|--------------|--------------|------------|---------------------|
| <b>Antioxidants</b> | SONGNOX® CS 1010 | ■                  | ■                  | ■            | ■            |            |                     |
|                     | SONGNOX® CS 1076 | ■                  | ■                  | ■            | ■            |            |                     |
|                     | SONGNOX® CS 2450 | ■                  | ■                  |              | ■            |            |                     |
|                     | SONGNOX® CS 1035 |                    | ■                  |              | ■            |            |                     |
|                     | SONGNOX® CS 1135 | ■                  | ■                  |              | ■            |            |                     |
|                     | SONGNOX® CS 4425 | ■                  | ■                  |              | ■            |            |                     |
|                     | SONGNOX® CS 1680 | ■                  | ■                  |              | ■            |            | ■                   |
|                     | SONGNOX® CS 6260 | ■                  | ■                  |              | ■            |            | ■                   |
|                     | SONGNOX® CS PQ   | ■                  | ■                  |              | ■            |            | ■                   |

Please ask the expert about additional antioxidants and blends.

|                                |                    | Automotive<br>Inks | Industrial<br>Wood | Construction | Solventborne | Waterborne | UV curing<br>Powder |
|--------------------------------|--------------------|--------------------|--------------------|--------------|--------------|------------|---------------------|
| <b>UV Absorbers<br/>(UVAs)</b> | SONGSORB® CS 1130  | ■                  | ■                  | ■            | ■            | ■          |                     |
|                                | SONGSORB® CS 928   | ■                  |                    | ■            | ■            |            | ■                   |
|                                | SONGSORB® CS 329   | ■                  |                    | ■            | ■            | ■          |                     |
|                                | SONGSORB® CS 328*  |                    | ■                  | ■            | ■            |            |                     |
|                                | SONGSORB® CS 326   | ■                  |                    | ■            | ■            | ■          |                     |
|                                | SONGSORB® CS 384-2 | ■                  | ■                  | ■            | ■            | ■          |                     |
|                                | SONGSORB® CS 900   | ■                  | ■                  | ■            |              |            | ■                   |
|                                | SONGSORB® CS 81    |                    |                    | ■            |              | ■          |                     |
|                                | SONGSORB® CS 312   | ■                  |                    | ■            |              | ■          | ■                   |
|                                | SONGSORB® CS 1577  | ■                  |                    | ■            |              | ■          |                     |
|                                | SONGSORB® CS 400   | ■                  |                    | ■            | ■            | ■          |                     |










\* Not available in Europe

|  |                   | Automotive<br>Inks | Industrial<br>Wood | Construction | Solventborne | Waterborne | UV curing<br>Powder |
|--|-------------------|--------------------|--------------------|--------------|--------------|------------|---------------------|
| <b>Hindered Amine<br/>Light Stabilizers<br/>(HALS)</b> | SONGSORB® CS 292  | ■                  | ■                  | ■            | ■            |            |                     |
|  | SONGSORB® CS 770  |                    | ■                  |              | ■            |            |                     |
|  | SONGSORB® CS 622  |                    | ■                  |              | ■            |            | ■                   |
|  | SONGSORB® CS 119  | ■                  | ■                  |              | ■            |            | ■                   |
|  | SONGSORB® CS 144  | ■                  | ■                  |              | ■            |            | ■                   |
|  | SONGSORB® CS 5100 |                    | ■                  | ■            | ■            |            |                     |
|  | SONGSORB® CS AQ01 | ■                  | ■                  | ■            | ■            | ■          |                     |

■ Recommended  
■ Suitable









# Antioxidants

|  |   | Molecular Weight | Melting Range (°C) | Solubility (g/100 g solvent at 25°C)  |
|--|---|------------------|--------------------|---|
| <b>SONGNOX® CS 1010</b><br>Tetrakis[methylene-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]methane<br>CAS NO. 6683-19-8<br>SL                         |    | 1178             | 110.0 ~ 125.0      | Squalane < 0.05<br>n-Hexane < 0.1<br>Acetone < 50.0<br>Ethanol < 0.1<br>Toluene 48.0<br>Xylene 24.2<br>Ethyl acetate > 50.0       |
| <b>SONGNOX® CS 1076</b><br>Octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate<br>CAS NO. 2082-79-3<br>SL  |    | 531              | 50.0 ~ 55.0        | Squalane 0.5<br>n-Hexane > 50.0<br>Acetone > 50.0<br>Ethanol < 0.1<br>Toluene > 50.0<br>Xylene > 50.0<br>Ethyl acetate > 50.0     |
| <b>SONGNOX® CS 1135</b><br>Benzenepropanoic acid, 3,5-bis(1,1-dimethylethyl)-4-hydroxy-, C7-9-branched alkyl esters<br>CAS NO. 125643-61-0<br>LQ         |    | 390              | —                  | Squalane > 50.0<br>n-Hexane > 50.0<br>Acetone > 50.0<br>Ethanol > 50.0<br>Toluene > 50.0<br>Xylene > 50.0<br>Ethyl acetate > 50.0 |
| <b>SONGNOX® CS 2450</b><br>Triethylene glycol-bis-3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionate<br>CAS NO. 36443-68-2<br>SL                        |   | 587              | 76.0 ~ 80.0        | Squalane < 0.05<br>n-Hexane < 0.1<br>Acetone > 50.0<br>Ethanol 9.0<br>Toluene 10.0<br>Xylene 0.5<br>Ethyl acetate > 50.0          |
| <b>SONGNOX® CS 1035</b><br>Thiodiethylene bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]<br>CAS NO. 41484-35-9<br>SL                               |  | 643              | > 65.0             | Squalane < 0.05<br>n-Hexane 0.8<br>Acetone > 50.0<br>Ethanol 1.1<br>Toluene > 50.0<br>Xylene > 50.0<br>Ethyl acetate > 50.0       |
| <b>SONGNOX® CS 4425</b><br>4,4'-Butylidenebis(6-tert-3-methylphenol)<br>CAS NO. 85-60-9<br>SL  |  | 383              | 208.0 ~ 214.0      | Squalane < 0.05<br>n-Hexane < 0.1<br>Acetone > 50.0<br>Ethanol 29.0<br>Toluene 1.0<br>Xylene < 0.1<br>Ethyl acetate > 50.0        |
| <b>SONGNOX® CS 1680</b><br>Tris(2,4-di-tert-butylphenyl) phosphite<br>CAS NO. 31570-04-4<br>SL   |  | 647              | 181.0 ~ 187.0      | Squalane < 0.05<br>n-Hexane 10.0<br>Acetone 1.3<br>Ethanol < 0.1<br>Toluene 25.0<br>Xylene 24.0<br>Ethyl acetate 5.0              |
| <b>SONGNOX® CS 6260</b><br>Bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite<br>CAS NO. 26741-53-7<br>SL  |  | 605              | 170.0 ~ 180.0      | Squalane < 0.05<br>n-Hexane 2.0<br>Acetone 3.0<br>Ethanol < 0.1<br>Toluene 26.0<br>Xylene 17.0<br>Ethyl acetate 0.7               |
| <b>SONGNOX® CS PQ</b><br>Phosphorous trichloride, reaction products with 1,1'-biphenyl and 2,4-bis(1,1-dimethylethyl)phenol<br>CAS NO. 119345-01-6<br>SL |  | 1035             | 75.0 ~ 100.0       | Squalane 0.1<br>n-Hexane > 50.0<br>Acetone 9.0<br>Ethanol < 0.1<br>Toluene > 50.0<br>Xylene > 50.0<br>Ethyl acetate > 50.0        |

# UV Absorbers (UVAs)

|  |  | Molecular Weight | Melting Range (°C) | Solubility (g/100 g solvent at 25°C)   |
|--|--|------------------|--------------------|--|
| <b>SONGSORB® CS 1130</b><br>Mixture of $\alpha$ -3-(3-(2H-benzotriazole-2-yl)-5-tert-butyl-4-hydroxyphenyl)-1-oxopropyl- $\omega$ -hydroxy poly(oxyethylene) and $\alpha$ -3-(3-(2H-benzotriazole-2-yl)-5-tert-butyl-4-hydroxy phenyl)-1-oxopropyl- $\omega$ -3-(3-(2H-benzotriazole-2-yl)-5-tert-butyl-4-hydroxyphenyl)-1-oxopropoxy poly(oxyethylene) and polyethyleneglycol<br>CAS NO. 104810-48-2 / 104810-47-1 / 25322-68-3<br>LQ |  | Mix              | –                  | Squalane < 0.05<br>n-Hexane < 1.00<br>Acetone > 50<br>Ethanol > 50<br>Toluene > 50<br>Xylene > 50<br>Ethyl acetate > 50                                      |
| <b>SONGSORB® CS 928</b><br>2-hydroxy-3-(1,1-dimethylbenzyl)-5-(1,1,3,3-tetramethylbutyl)phenyl]-2Hbenzotriazole<br>CAS NO. 73936-91-1<br>SL  |  | 442              | 110.0 ~ 113.0      | Squalane 0.15<br>n-Hexane 10.10<br>Acetone 10.20<br>Ethanol 0.15<br>Toluene > 50<br>Xylene > 50<br>Ethyl acetate 28.6  |
| <b>SONGSORB® CS 329</b><br>2-(2H-benzotriazole-2-yl)-4-(1,1,3,3-tetramethylbutyl)phenol<br>CAS NO. 3147-75-9<br>SL   |  | 323              | 103.0 ~ 105.0      | Squalane 0.3<br>n-Hexane 6.0<br>Acetone 11.5<br>Ethanol < 0.1<br>Toluene 44.7<br>Xylene 49.0<br>Ethyl acetate 21.3   |
| <b>SONGSORB® CS 328</b><br>2-(2'-hydroxy-3',5'-di-t-amylphenyl) benzotriazole<br>CAS NO. 25973-55-1<br>SL  |  | 352              | 80.0 ~ 88.0        | Squalane 3.3<br>n-Hexane 20.0<br>Acetone 8.0<br>Ethanol 0.3<br>Toluene < 50.0<br>Xylene < 50.0<br>Ethyl acetate 30.0   |
| <b>SONGSORB® CS 326</b><br>2-(2'-hydroxy-3'-tert-butyl-5'-methylphenyl)-5-chlorobenzotriazole<br>CAS NO. 3896-11-5<br>PW   |  | 316              | 138.0 ~ 141.0      | Squalane 0.7<br>n-Hexane 1.5<br>Acetone 1.5<br>Ethanol 0.1<br>Toluene 10.4<br>Xylene 11.8<br>Ethyl acetate 3.2   |
| <b>SONGSORB® CS 384-2</b><br>Benzenepropanoic acid, 3-(2H-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy-, C7-9 branched and linear alkyl esters with 4-7% 1-methoxy-2-propyl acetate<br>CAS No. 127519-17-9<br>LQ   |  | 451.6            | –                  | Squalane > 50.0<br>n-Hexane > 50.0<br>Acetone > 50.0<br>Ethanol 0.11<br>Toluene > 50.0<br>Xylene > 50.0<br>Distilled Water Insoluble<br>Ethyl Acetate > 50.0 |
| <b>SONGSORB® CS 900</b><br>2-[2-hydroxy-3,5-di(1,1-dimethylbenzyl)phenyl]-2H-benzotriazole<br>CAS NO. 70321-86-7<br>SL   |  | 448              | 138.0 ~ 142.0      | Squalane < 0.05<br>n-Hexane < 0.1<br>Acetone 2.5<br>Ethanol < 0.1<br>Toluene 18.1<br>Xylene 13.1<br>Ethyl acetate 5.1  |
| <b>SONGSORB® CS 81</b><br>2-hydroxy-4-n-octoxybenzophenone<br>CAS NO. 1843-05-6<br>SL  |  | 326              | > 47.0             | Squalane 0.3<br>n-Hexane 18.0<br>Acetone > 50.0<br>Ethanol 1.0<br>Toluene > 50.0<br>Xylene > 50.0<br>Ethyl acetate > 50.0                                    |
| <b>SONGSORB® CS 312</b><br>N-(2-ethoxyphenyl)-N'-(2-ethylphenyl) ethanediamide<br>CAS NO. 23949-66-8<br>SL   |  | 312              | 124.0 ~ 128.0      | Squalane < 0.05<br>n-Hexane < 0.1<br>Acetone 4.0<br>Ethanol < 0.1<br>Toluene 7.3<br>Xylene 5.2<br>Ethyl acetate 5.0  |
| <b>SONGSORB® CS 1577</b><br>2-(4,6-diphenyl-1,3,5-triazine-2-yl)-5-hexyloxy phenol<br>CAS NO. 147315-50-2<br>SL  |  | 425              | 147.0 ~ 151.0      | Squalane < 0.05<br>n-Hexane < 0.1<br>Acetone 0.2<br>Ethanol < 0.1<br>Toluene 6.3<br>Xylene 5.5<br>Ethyl acetate 0.8  |
| <b>SONGSORB® CS 400</b><br>Mixture of 2-[4-[(2-Hydroxy-3-dodecyloxypropyl)oxy]-2-hydroxyphenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine<br>CAS No. 153519-44-9<br>LQ  |  | 646              | –                  | Squalane < 0.05<br>n-Hexane > 50.0<br>Acetone > 50.0<br>Ethanol 0.5<br>Toluene > 50.0<br>Xylene > 50.0<br>Distilled Water Insoluble<br>Ethyl Acetate > 50.0  |

# Hindered Amine Light Stabilizers (HALS)

|  |   | Molecular Weight                  | Melting Range (°C)       | Solubility (g/100 g solvent at 25°C)  |
|--|---|-----------------------------------|--------------------------|---|
| <b>SONGSORB® CS 292</b><br>Mixture of bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-sebacate and 1-(methyl)-8-(1,2,2,6,6-pentamethyl-4-piperidinyl)-sebacate<br>CAS NO. 41556-26-7 / 82919-37-7<br>LQ   |    | 509/370                           | –                        | Squalane > 50.0<br>n-Hexane > 50.0<br>Acetone > 50.0<br>Ethanol > 50.0<br>Toluene > 50.0<br>Xylene > 50.0<br>Ethyl acetate > 50.0   |
| <b>SONGSORB® CS 770</b><br>Bis(2,2,6,6-tetramethyl-4-piperidinyl) sebacate<br>CAS NO. 52829-07-9<br>SL   |    | 481                               | 81.0 ~ 85.0              | Squalane < 0.05<br>n-Hexane < 0.1<br>Acetone 35.0<br>Ethanol > 50.0<br>Toluene > 50.0<br>Xylene 49.0<br>Ethyl acetate 38.1          |
| <b>SONGSORB® CS 622</b><br>Polymer of dimethyl succinate and 4-hydroxy-2,2,6,6-tetramethyl-1-piperidine ethanol<br>CAS NO. 65447-77-0<br>SL  |    | 3100 ~ 4000                       | > 55.0 (softening point) | Squalane < 0.05<br>n-Hexane < 0.1<br>Acetone 39.0<br>Ethanol < 0.1<br>Toluene 7.1<br>Xylene 35.0<br>Ethyl acetate 21.0              |
| <b>SONGSORB® CS 119</b><br>1,3,5-triazine-2,4,6-triamine, N2,N2''-1,2-ethanediylbis [N2-[3-[[4,6-bis[butyl (1,2,2,6,6-pentamethyl-4-piperidinyl)amino]-1,3,5-triazin-2-yl]amino]propyl]-N',N''-dibutyl-N',N''-bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-<br>CAS NO. 106990-43-6<br>PS |   | 2286                              | 115.0 ~ 150.0            | Squalane < 0.05<br>n-Hexane < 0.1<br>Acetone 0.2<br>Ethanol < 0.1<br>Toluene 25.0<br>Xylene 24.0<br>Ethyl acetate 0.9               |
| <b>SONGSORB® CS 144</b><br>Bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-[[3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]methyl]butylmalonate<br>CAS NO. 63843-89-0<br>SL  |  | 685                               | 146.0 ~ 150.0            | Squalane < 0.05<br>n-Hexane 1.70<br>Acetone 3.00<br>Ethanol 0.33<br>Toluene 21.9<br>Xylene 13.2<br>Ethyl acetate 5.4                |
| <b>SONGSORB® CS 5100</b><br>Decanedioic acid, bis(2,2,6,6-tetramethyl-1-(octyloxy)-4-piperidinyl)ester, reaction products with 1,1-dimethylethylhydroperoxide and octane<br>CAS NO. 129757-67-1<br>LQ  |  | 737                               | –                        | Squalane > 50<br>n-Hexane > 50<br>Acetone > 50<br>Ethanol 0.60<br>Toluene > 50<br>Xylene > 50<br>Ethyl acetate > 50                 |
| <b>SONGSORB® CS AQ01</b><br>POE (n) 2,2,6,6-tetramethyl-4-piperidinol<br>CAS No. Proprietary<br>LQ   | Proprietary information   | Polymer, confidential information | –                        | Squalane < 0.05<br>n-Hexane < 0.05<br>Acetone > 50<br>Ethanol > 50<br>Toluene 14<br>Xylene > 50<br>Ethyl acetate > 50<br>Water > 50 |

# Light and heat stabilization formulations guide

|                    | Antioxidants (AOs)  | UV Absorbers (UVAs)                           | Hindered Amine Light Stabilizers (HALS)  |
|--------------------|---|---|--|
| <b>Mechanism</b>   | Deactivate free radicals                                    | Convert UV into heat                          | Deactivate free radicals   |
| <b>Application</b> | Interior / Exterior   | Interior / Exterior                           | Exterior   |
| <b>Protection</b>  | Thermal oxidation   | Photo oxidation and degradation               | Photo degradation  |
| <b>Prevention</b>  | Yellowing<br>Loss of mechanical properties<br>Embrittlement | Yellowing<br>Loss of adhesion<br>Blistering   | Loss of mechanical properties<br>Surface defects<br>Pigment fading<br>Loss of water impermeability |
| <b>Field</b>       | Coating   | Underneath substrate<br>Deeper coating layers | Coating surface<br>Pigments for coatings   |

| Film Thickness | UVA     |
|----------------|---------|
| 10 ~ 20 µm     | 8 ~ 4 % |
| 20 ~ 40 µm     | 4 ~ 2 % |
| 40 ~ 80 µm     | 2 ~ 1 % |

| Pigmentation     | HALS          | UVA (*)       |
|------------------|---------------|---------------|
| opaque           | 1.0 % ~ 2.0 % | 0.0 % ~ 0.5 % |
| semi-transparent | 0.5 % ~ 1.5 % | 0.5 %         |
| clear            | 0.5 % ~ 1.0 % | 1.0 % ~ 1.5 % |

% of binder solid  
 (\*) % UVA based on dry film thickness of 40 µm  
 % UVA depends on the pigments used




# Standard Packaging

- **Antioxidants, Solids:** 25 kg Carton Box  
20 kg PE Bag (20 kg aluminum coated bags for SONGNOX® CS 6260, SONGNOX® CS PQ)
- **Antioxidants, Liquids:** 185 kg Steel Drum  
25 kg PE Drum
- **HALS, Solids:** 20 kg PE Bag  
25 kg Carton Box
- **HALS, Liquids:** 25 kg PE Drum  
200 kg Steel Drum  
900 kg IBC
- **UV Absorbers, Solids:** 20 kg Carton Box  
25 kg Carton Box
- **UV Absorbers, Liquids:** 25 kg PE Drum  
200 kg Steel Drum

Standard pallet size is CP1.

## Key to Abbreviations of Physical Forms

- **PW:** Powder
- **SB:** Semi Bead
- **SL:** Solid
- **FF:** Free Flow
- **DW:** Dispersion
- **MB:** Micro Beads
- **FC:** Fusion Crystal
- **LQ:** Liquid or Molten
- **BD:** Beads
- **DF:** Dust Free Flow
- **CP:** Crystalline Powder
- **PS:** Pastilles
- **GR:** Granule
- **FG:** Fine Grind
- **VL:** Viscous Liquid



## Transport and Storage

As a general guideline, we recommend storing the products mentioned in this brochure in their original sealed containers in a cold and dry place. For more detailed information on a specific product, please refer to the corresponding **Technical Data Sheet**.

By law, a number of chemical products must be labeled in respect of transport, storage and handling. Thus corresponding care is a prerequisite for their appropriate handling. Furthermore, local legal regulations may apply.

Detailed information is given in the respective **Safety Data Sheets**.



# About SONGWON Industrial Group

SONGWON, which was founded in 1965 and is headquartered in Ulsan, South Korea, is a leader in the development, production and supply of specialty chemicals.

The second largest manufacturer of polymer stabilizers worldwide, SONGWON operates group companies all over the world, offering the combined benefits of a global framework and readily accessible local organizations.

Dedicated experts work closely together with customers to develop tailor-made solutions that meet individual requirements.

For further information, please go to:  
**[www.songwon.com](http://www.songwon.com)**





For further information, please go to:

**[www.songwon.com](http://www.songwon.com)**

[specialtychemicals@songwon.com](mailto:specialtychemicals@songwon.com)

SONGWON provides customers with warranties and representations as to the chemical or technical specifications, compositions and/or the suitability for use for any particular purpose exclusively in individual written agreements.

The facts and figures contained herein have been carefully compiled to the best of SONGWON's knowledge but are essentially intended for informational purposes only.

SONGWON Industrial Group does not accept any liability whatsoever for any information, reference or advice provided in this document or any similar SONGWON publication.

Version 3, February 2018 (Specialty Chemicals)